

# Desmodur<sup>®</sup> N 75 MPA/X

<b>Characterization</b>	Aliphatic polyisocyanate (HDI biuret). As the hardener component for lightfast polyurethane coating systems.
<b>Form supplied</b>	approx. 75 % in 1-methoxypropylacetate-2/xylene, 1 : 1

Specification Property	Value	Unit of measurement	Method
NCO content	16.5 ± 0.3	%	M105-ISO 11909
Non-volatile content 2.2 g / 120 min / 100 °C	75 ± 1	%	M020-ISO 3251
Viscosity at 23 °C	250 ± 75	mPa·s	M014-ISO 3219/A.3
Color value (Hazen)	≤ 40		M017-EN 1557
Monomeric HDI	< 0.38	%	M106-ISO 10283

Other data* Property	Value	Unit of measurement	Method
Viscosity at 25 °C	approx. 225	mPa·s	M014-ISO 3219/A.3
Equivalent weight	approx. 255		
Flash point	approx. 38	°C	DIN 53 213/1
Density at 20 °C	approx. 1.07	g/ml	DIN EN ISO 2811

\*These values provide general information and are not part of the product specification.

# Desmodur<sup>®</sup> N 75 MPA/X

## Solubility / thinnability

Desmodur<sup>®</sup> N 75 MPA/X can be thinned with esters, ketones and aromatic hydrocarbons such as ethyl acetate, butyl acetate, methoxypropylacetate, acetone, methyl ethyl ketone, methyl isobutyl ketone, cyclohexanone, toluene, xylene, solvent naphtha<sup>®</sup> 100 and mixtures thereof.

Generally speaking, it has good compatibility with the solvents listed. However, the solutions formed must be tested for their storage stability. Only PU grade solvents should be used (max. 0.05 % water, absence of reactive groups such as hydroxyl or amino groups). Aliphatic hydrocarbons are unsuitable as solvents.

Desmodur<sup>®</sup> N 75 MPA/X should not be thinned to below a solids content of 40 %. Prolonged storage of a solution with a lower binder content may result in turbidity and sedimentation.

---

## Compatibility

Generally speaking, Desmodur<sup>®</sup> N 75 MPA/X can be mixed with the following products: aliphatic polyisocyanates such as Desmodur<sup>®</sup> N 3200, N 3300, N 3400, N 3600 and Desmodur<sup>®</sup> Z 4470; aromatic polyisocyanates such as Desmodur<sup>®</sup> L, HL and IL; polyester polyols such as Desmophen<sup>®</sup> 651, 670 and polyacrylates; polyether polyols such as Desmophen<sup>®</sup> 1380 BT. However, the compatibility of the combinations used should always be tested.

---

## Properties / Applications

Desmodur<sup>®</sup> N 75 MPA/X is used primarily as the hardener component for lightfast two-component polyurethane coatings with high resistance to chemicals and weathering, very good gloss retention and outstanding mechanical properties. Preferred co-reactants are polyacrylate or polyester polyols.

The main applications for systems based on Desmodur<sup>®</sup> N 75 MPA/X are as air- and force-drying coatings for automotive and industrial finishing, for wood, furniture and plastics and for corrosion protection.

# Desmodur<sup>®</sup> N 75 MPA/X

## Storage

- Storage in original sealed Covestro container.
- Recommended storage temperature: 5 - 25 °C.
- Protect from moisture, heat and foreign material.

General information: The product is sensitive to moisture. Storage at higher temperatures will result in increase of color and viscosity.

---

## Storage time

Covestro represents that, for a period of nine months following the day of shipment as stated in the respective transport documents, the product will meet the specifications or values set forth in section "specifications or characteristic data" above, what ever is applicable, provided that the product is stored in full compliance with the storage conditions set forth in and referenced under section "storage" above and is otherwise handled appropriately.

The lapse of the nine months period does not necessarily mean that the product no longer meets specifications or the set values. However, prior to using said product, Covestro recommends to test such a product if it still meets the specifications or the set values. Covestro does not make any representation regarding the product after the lapse of the nine months period and Covestro shall not be responsible or liable in any way for the product failing to meet specifications or the set values after the lapse of the nine months period.

# Desmodur<sup>®</sup> N 75 MPA/X

**Labeling and statutory requirements** This product data sheet is only valid in conjunction with the latest edition of the corresponding Safety Data Sheet. Any updating of safety-relevant information – in accordance with statutory requirements – will only be reflected in the Safety Data Sheet, copies of which will be revised and distributed. Information relating to the current classification and labeling, applications and processing methods and further data relevant to safety can be found in the currently **valid Safety Data Sheet**.

**Further information** The product is used mainly as a hardener in coating materials or adhesives. The handling of coating materials or adhesives containing reactive polyisocyanates and residual **monomeric HDI** requires appropriate protective measures referred to in the safety data sheet. These products may therefore be used only in industrial or trade applications. **They are not suitable for use in homemaker (DIY) applications.**

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

This product is not designated as „Medical Grade“ (1) and therefore shall not be considered a candidate for the manufacture of a medical device or of intermediate products for medical devices, which are intended under normal use to be brought into direct contact with the patient's body (e.g., skin, body fluids or tissues, including indirect contact to blood)\*. This product is also not designated for Food Contact (2), including drinking water, or cosmetic applications. If the intended use of the product is for the manufacture of a medical device or of intermediate products for medical devices, for Food Contact products or cosmetic applications Covestro must be contacted in advance to provide its agreement to sell such product for such purpose. Nonetheless, any determination as to whether a product is appropriate for use in a medical device or intermediate products for medical devices, for Food Contact products or cosmetic applications must be made solely by the purchaser of the product without relying upon any representations by Covestro.

1) Please see the "Guidance on Use of Covestro Products in a Medical Application" document.

2) As defined in Commission Regulation (EU) 1935/2004.

Editor: Coatings, Adhesives & Specialties  
Covestro AG  
Kaiser-Wilhelm-Allee 60  
51373 Leverkusen, Germany  
[www.covestro.com](http://www.covestro.com)

**Contact:**  
CAS Single Point of Contact EMEA  
e-mail: [cas\\_spoc\\_emea@covestro.com](mailto:cas_spoc_emea@covestro.com)