

Technical Data Sheet

Eastman™ Chlorinated Polyolefin 343-3 (50% Solids in Xylene)

Application/Uses

- Adhesion promoter for inks
- Adhesion promoter for paints
- Automotive OEM
- Coatings
- Coatings for Automotive Plastics
- Coatings for plastic
- Printing Inks

Product Description

Eastman™ Chlorinated Polyolefin 343-3 is a 50% solution of a chlorinated polyolefin in xylene. It is 26-32 wt. % chlorine and has a Gardner color value of 11. Chlorinated Polyolefin 343-3 has a good solvent tolerance for a wide range of solvents.

Typical Properties

Property	Typical Value, Units
Specific Gravity @ 25°C/25°C	0.986
Flash Point Tag Closed Cup	27°C (80°F)
Color, Gardner	11
Chlorine	26-32 wt %
Specific Gravity, Solid CPO @ 25°C/25°C	1.108

Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

09-May-2001 3:18:00 PM